

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (currently amended) A photothermographic material comprising a preformed photosensitive silver halide, a reducing agent for reducing silver ions, a binder and a non-photosensitive organic silver salt prepared in the presence of the preformed photosensitive silver halide, wherein the photosensitive silver halide has a silver iodide content ranging from 40 mol% to 100 mol%, and has a particle size ranging from 5 nm to 80 nm, and wherein the resulting non-photosensitive organic silver salt includes the preformed ~~is prepared in the presence of the~~ photosensitive silver halide ~~which has been preformed, such that the non-photosensitive organic silver salt includes the photosensitive silver halide.~~

2. (original) The photothermographic material according to claim 1, wherein the non-photosensitive organic silver salt including the photosensitive silver halide is produced by adding an alkali metal salt to an organic acid to prepare an alkali metal soap of at least a part of the organic acid, mixing the prepared alkali metal soap with the photosensitive silver halide, and thereafter admixing therewith a water-soluble silver salt.

3. (original) The photothermographic material according to claim 1, wherein the non-photosensitive organic silver salt has a silver behenate content ranging from 40 mol% to 70 mol%.
4. (original) The photothermographic material according to claim 2, wherein the non-photosensitive organic silver salt has a silver behenate content ranging from 40 mol% to 70 mol%.
5. (original) The photothermographic material according to claim 1, wherein the binder is polyvinyl butyral.
6. (original) The photothermographic material according to claim 1, wherein methyl ethyl ketone is used as a solvent for a coating solution, and a residual amount of the methyl ethyl ketone ranges from 0.1 mg/m² to 150 mg/m².
7. (original) The photothermographic material according to claim 1, wherein the photosensitive silver halide has a particle size ranging from 5 nm to 50 nm.
8. (original) The photothermographic material according to claim 1, further comprising a compound selected from compounds of the following types 1 to 5:
(Type 1)
a compound that can be one-electron oxidized to produce a

one-electron oxidation product, which releases two or more electrons through a bond cleaving reaction;

(Type 2)

a compound that has two or more adsorptive groups to the silver halide in the same molecular structure and can be one-electron oxidized to produce a one-electron oxidation product which further releases one electron through a bond cleaving reaction;

(Type 3)

a compound that can be one-electron oxidized to produce a one-electron oxidation product, which releases additional one or more electrons after a bond forming process;

(Type 4)

a compound that can be one-electron oxidized to produce a one-electron oxidation product, which releases additional one or more electrons after an intra-molecular ring opening reaction; and

(Type 5)

a compound represented by X-Y, in which X represents a reducing group and Y represents a leaving group, wherein the reducing group X can be one-electron oxidized to produce a one-electron oxidation product, which leaves Y to produce X radical through an X-Y bond cleaving reaction, followed by releasing one more electrons from the X radical.

9. (original) The photothermographic material according to claim 2, further comprising a compound selected from compounds of the following types 1 to 5:

(Type 1)

a compound that can be one-electron oxidized to produce a one-electron oxidation product, which releases two or more electrons through a bond cleaving reaction;

(Type 2)

a compound that has two or more adsorptive groups to the silver halide in the same molecular structure and can be one-electron oxidized to produce a one-electron oxidation product which further releases one electron through a bond cleaving reaction;

(Type 3)

a compound that can be one-electron oxidized to produce a one-electron oxidation product, which releases additional one or more electrons after a bond forming process;

(Type 4)

a compound that can be one-electron oxidized to produce a one-electron oxidation product, which releases additional one or more electrons after an intra-molecular ring opening reaction; and


(Type 5)

a compound represented by X-Y, in which X represents a reducing group and Y represents a leaving group, wherein the reducing group X can be one-electron oxidized to produce a one-electron oxidation product, which leaves Y to produce X radical through an X-Y bond cleaving reaction, followed by releasing one more electrons from the X radical.

10. (original) The photothermographic material according to claim 1,

further comprising a compound represented by formula (H):


Formula (H)



wherein Q represents an alkyl group, an aryl group or a heterocyclic group; Y represents a bivalent linking group; n represents 0 or 1; Z₁ and Z₂ represent a halogen atom; and X represents a hydrogen atom or an electron attractive group.

11. (previously presented) The photothermographic material according to claim 2, further containing a compound represented by formula (H):

Formula (H)




wherein Q represents an alkyl group, an aryl group or a heterocyclic group; Y represents a bivalent linking group; n represents 0 or 1; Z₁ and Z₂ represent a halogen atom; and X represents a hydrogen atom or an electron attractive group.

12. (original) The photothermographic material according to claim 1, wherein the reducing agent is a bisphenol-type reducing agent.

13. (original) The photothermographic material according to claim 1, further comprising a compound represented by formula (J):


Formula (J)



wherein R^{21} to R^{23} each independently represent an alkyl group, an aryl group, an alkoxy group, an aryloxy group, an amino group or a heterocyclic group.

14. (original) The photothermographic material according to claim 2, further comprising a compound represented by formula (J):

Formula (J)



wherein R^{21} to R^{23} each independently represent an alkyl group, an aryl group, an alkoxy group, an aryloxy group, an amino group or a heterocyclic group.

15. (original) The photothermographic material according to claim 1, further comprising a development accelerator.

16. (original) The photothermographic material according to claim 2, further comprising a development accelerator.

17. (original) The photothermographic material according to claim 15,

wherein the development accelerator is a hydrazine-based or naphthol-based compound.

18. (original) The photothermographic material according to claim 1, wherein the photosensitive silver halide has a silver iodide content ranging from 80 mol% to 100 mol%.

19. (original) The photothermographic material according to claim 1, wherein the photosensitive silver halide has a silver iodide content ranging from 85 mol% to 100 mol%.

20. (original) The photothermographic material according to claim 1, wherein the photosensitive silver halide has a silver iodide content ranging from 90 mol% to 100 mol%.